



Quick Prep General Purpose Acrylic Undercoat

Quick Prep is primarily designed for timber substrates where a high quality finish is required such as doors and window trim.

Product features

- High adhesion – particularly suitable for coating difficult surfaces
- Self levelling – dries to a smooth finish
- Sands readily if required for a very smooth finish
- Suitable for both interior and exterior applications

Typical areas of use

- Timber cladding
- Timber joinery
- Custom wood
- MDF
- Pressed chip board
- Polyurethane surfaces
- Enamel surfaces

Precautions

When used in exterior applications Quick Prep must be over coated within 6 months

Environmental qualities

- Manufactured in a carbon neutral certified facility – ISO 14064-1
- VOC 9 gms per litre EC07-13
- Ecolabel certified – Environmental Choice EC07-13
- Licence number 0703012

Colour

Standard colour is white, may be tinted to light pastel colours

Safety

- Read label before use and keep out of reach of children.
- If medical advice is needed: have product container or label at hand.
- Wear protective clothing such as overalls, goggles and gloves and ventilate working areas.
- Wash any paint deposits off skin.
- If sanding wear face mask to avoid inhaling dust particles.

Surface preparation

- General preparation of the surface to be painted should be completed before commencing application.
- All loose material must be removed and surface damage or imperfections made good.
- The surface must be clean, dry and free of contaminants.
- Areas with a build up of grime must be cleaned with sugar soap or quality equivalent.
- Previously painted enamel and polyurethane – sand to remove gloss and clean with a lint free cloth

Application schedule

Touch dry 15 minutes

Re-coat time (minimum) 2 hours

Practical coverage 10–12 square meters per litre

Dry film thickness @ 10 square meters per litre

42 microns per coat

Required number of coats – 1

Application is not recommended if the surface and/or air temperature is less than 10°C or is liable to fall below 10°C during the drying period

Application methods

Good quality paint or cutting in brush

Medium nap roller 10mm–14mm

Airless spray minimum 133 bars (2,000lb/sq in)

Tip size 17thou

Clean up and thinning

Clean up all equipment with water.

PaintPlus Quick Prep may be thinned to avoid exceeding application rates. Up to 50mls of water per litre may be added for this purpose.

Excessive thinning will lengthen drying times and have a detrimental impact on opacity and handling characteristics.